

Technical Properties of **SUR-fex[®] SC100**

Liquid Component Properties	Value
Polymer	Water Based Polyurethane
Density	8 -10 lbs/Gallon
Percent Solids	39 - 42
Brookfield Viscosity @ 25 deg C	25,000 – 35,000 cps (#6 Spindle @ 20 RPM)
PH	8.5 – 9.5

Product Availability

- Supplied Clear or Pigmented
- Applied to Fabric, Foams, or Composites
- Rotary Screen Printed
- Oven Cured
- Continuous Direct Cast Roll to Roll
- Full Coverage up to 66" Widths

Characteristics

- Medium Soft Hand
- Good Adhesion
- Durable
- Water Resistant

Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.