

Typical Properties of SUR-fex® NS100

Polymer	Polyurethane	
Physical Property	Test Method	Result
2A Wash Test	AATCC-61	Pass
Static Coefficient of Friction (Hex Pattern)	ASTM D1894	.940
Kinetic Coefficient of Friction (Hex Pattern)	ASTM D1894	1.002
Static Coefficient of Friction (Full Coat)	ASTM D1894	.871
Kinetic Coefficient of Friction (Full Coat)	ASTM D1894	.868

Product Availability

- Full coverage or patterns up to 66" width and .020" Thickness
- Direct cast to fabrics, foams or nonwovens
- 3D and Tactile Effects
- Continuous Roll-to-Roll

Characteristics

- Excellent Durability
- Enhanced Coefficient of Friction
- Abrasion Resistant
- Washable
- Cold Crack Resistant
- Spacer Functionality

Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

